

Tarkofoam II / Tarkoflex II



Product Information

WOOD

	15 m2	75 m2
Tarkofoam II	8790311	8790310
Tarkoflex II	8790312	8790313

Tarkett foam underlay is used for floating installation as an impact sound insulation and also to give some comfort when walking on the floor. It will level out minor irregularities in the sub floor. If you have moisture in your sub floor, a damp proof membrane is always required, so in that case use the Tarkoflex II. Use the chart as a guide to choose correct underlay. For more exact information please contact your floor dealer.

Concrete	Tarkoflex II
Tiles	
Under-floor heating	
Shipboard	Tarkofoam II
Existing wooden floor	

Tarkofoam II - 2 mm thick Polyethylene foam

Tarkoflex II - 2 mm thick Polyethylene foam with a 100 micron moisture barrier film

Physical Properties	Test method	Unit	Value
Normal Foam Density	ISO 845	kg/m ³	30
Nominal Foam Thickness		mm	2
Compressive strength @ 25% deformation @ 50% deformation	DIN 53577	ton/m ²	2,4 8,3
Compression Set (recovery)	ASTM 3575-B	%	30
Tear Strength MD TD	ASTM D624-86	KN/m	1,29 1,82
Thermal Conductivity	ISO 8301	W/mK	0,05
Heat Resistance	ISO 8301	m2K/W	0,04
Water Vapour Resistance Tarkofoam II	SS0212582	S/m Sd(m)	2,31x10 ⁵ 6,1
Water Vapour Resistance Tarkoflex II	SS0212582	S/m Sd(m)	3,35x10 ⁶ 92
Impact Sound Insulation	EN ISO 140-8 EN ISO 717-2	dB	17-19
Ageing Resistance	SP 0414 ISO 1798	Year	50

