


Product
Datasheet
2010



WOOD

Professional



WOOD

Professional



TECHNICAL INFORMATION

Professional

Thickness	13/14 mm	22 mm
Width	188	188
Length	2018/2525	2525
Wearlayer thickness (mm)	app. 2,5/3,6	app. 3,6
Weight (kg/m ²)	app. 7,2/8,0	app. 14,8
Taber Abraser/Lacquer's wear resistance*		
prEN 13696		
abrasion penetration Proteco Lacq.(revs)	>4000	>4000
abrasion penetration Proteco Nat.(revs)	>3500	>3500
abrasive wear (mg/100revs)	app. 3,5	app. 3,5
Reduction of sound weighted index		
index "footfall" to the room below.		
NF EN ISO 140-8 / Acc to NF EN ISO 717-2,		
ΔL_w in dB with 2 mm Tarkofoam/flex II	17	17
Formaldehyde emission		
EN 13986	E1	E1
Reaction to Fire		
EN 13501	D _{fl}	D _{fl}
Thermal insulation value		
(RT m ² K/W)		
board only	0,101	0,152
with rag felt	0,121	0,182
with 2 mm Tarkofoam/flex II	0,141	0,192
Installation**	Floating / Glue down	Floating / Glue Down
Underfloor heating compatible***	Maximum floor surface temperature 27°C with self-regulating under-floor heat system.	

* Data show results with new components according to 2006 update. Method not applicable for brushed products due to the structured surface.

** Contact your flooring supplier for further information

*** Not suitable for the woodspecies beech and maple.

Professional 13 mm

3-strip 13 x 2018 x 188	Lacquer Ultraloc	Natura Ultraloc
Oak Nature	•	•

Professional 14 mm

3-strip 14 x 188	Lacquer Ultraloc L:2018 mm	Natura Ultraloc L:2018 mm	Lacquer Tongue & Groove L:2525 mm
Oak Nature	•	•	•
Beech Nature			•

Professional 22 mm

3-strip 22 x 2525 x 188 mm	Lacquer Tongue & Groove
Oak Nature	•
Ash Nature	•